

# BOUNTY

	AERO		BORNEO		LAURA		LIMBY		SCARLET		ZARA	
SESTAVA TKANINE COMPOSITION SIROVINSKI SASTAV TKANINE ZUSAMMENSETZUNG COMPOSIZIONE TESSUTO	100% POLIESTER 100% POLYESTER		52% POLIESTER, 41% AKRIL, 7% LAN 52% POLYESTER, 41% ACRYLIC, 7% LINEN		82% POLIESTER, 11% BOMBAŽ, 7% LAN 82% POLYESTER, 11% COTTON, 7% LINEN		53% POLIESTER, 39% AKRIL, 8% LAN 53% POLYESTER, 39% ACRYLIC, 8% LINEN		100% POLIESTER 100% POLYESTER		89,5% POLIESTER, 10,5% LAN 89,5% POLYESTER, 10,5% LINEN	
ŠIRINA/WIDTH/ŠIRINA/BREITE/ ALTEZZA	140 cm +/-2%		140 cm +/-2%		140 cm +/-2%		140 cm +/-2%		140 cm +/-2%		140 cm +/-2%	
TEŽA/WEIGHT/TEŽINA/GEWICHT/PESO	571 g/m <sup>2</sup> +/-5%		535 g/m <sup>2</sup> +/-5%		490 g/m <sup>2</sup> +/-5%		453 g/m <sup>2</sup> +/-5%		478 g/m <sup>2</sup> +/-5%		589 g/m <sup>2</sup> +/-5%	
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE EN ISO 13934-1: 2013	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA
	1847 N	1574 N	2764 N	1550 N	2261 N	475 N	2687 N	744 N	2101 N	1534 N	2627 N	1551 N
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE EN ISO 13937-3: 2000	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA
	230 N	167 N	390 N	285 N	459 N	140 N	90 N	272 N	94 N	64 N	542 N	449 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA EN ISO 13936-2: 2004	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA	OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA
	0,9 mm	0,5 mm	1 mm	4 mm	2,2 mm	4,2 mm	1,2 mm	1,0 mm	1,9 mm	0	3,0 mm	1,1 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLIJANJE SCHEUERBESTÄNDIGKEIT RESISTENZA ALL'ABRASIONE EN ISO 12947-2: 1999	31.000		80.300		50.000		92.000		15.000		22.000	
	OBRATOV/REVS./OBRATAJA/TOUREN/GIRI		OBRATOV/REVS./OBRATAJA/TOUREN/GIRI		OBRATOV/REVS./OBRATAJA/TOUREN/GIRI		OBRATOV/REVS./OBRATAJA/TOUREN/GIRI		OBRATOV/REVS./OBRATAJA/TOUREN/GIRI		OBRATOV/REVS./OBRATAJA/TOUREN/GIRI	
PILING/PILLING RESISTANCE/PILING/ PILLBILDUNG/RESISTENZA PILLING EN ISO 12945-2: 2000	4-5		4		5		4-5		5		4-5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE EN ISO 105-B02: 2014	5		4-5		5		5		5		5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLIJANJE REIBECHTHEIT RESISTENZA COLORE ALL'ABRASIONE EN ISO 105-X12: 2016	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/ UMIDO	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/ UMIDO	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/ UMIDO	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/ UMIDO	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/ UMIDO	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/ UMIDO
	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5
VSEBNOŠT AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI 64 LFG 82.02.2&3&4: 2004	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOŠT BARVIL, KI POVZROČAJO ALERGIJE ALLERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLORANTI ALLERGENICI DIN 54231: 2005	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO BS 5852: 1979 Part 1	PRESTAL PASSED PROŠAO BESTANDEN SUPERATO		PRESTAL PASSED PROŠAO BESTANDEN SUPERATO		PRESTAL PASSED PROŠAO BESTANDEN SUPERATO		PRESTAL PASSED PROŠAO BESTANDEN SUPERATO		PRESTAL PASSED PROŠAO BESTANDEN SUPERATO		PRESTAL PASSED PROŠAO BESTANDEN SUPERATO	